



## Transformer Oil

Conoco Transformer Oil is a highly refined electrical insulating oil developed for use in oil-immersed transformers, capacitors, tap changers and circuit breakers where the equipment manufacturer specifies a Type II inhibited oil.

Transformer Oil is available in one viscosity grade: ISO 10. It is formulated with hydrotreated naphthenic base oils and an oxidation inhibitor to minimize sludge and deposit formation and provide extended service life compared with non-inhibited transformer oils. It has a high dielectric strength and low power factor to provide excellent insulating properties. It has excellent low-temperature properties and is noncorrosive to copper and copper alloys. This product does **not** contain any PCBs.

### **Applications**

- Oil-immersed transformers
- Circuit breakers
- Fuses
- Switches
- Tap changers
- Oil-immersed electrical equipment

Transformer Oil meets the performance requirements or specifications of the following professional societies that oversee transformer oils:

- ANSI/ASTM D3487 Type II Inhibited Oil
- British Standard BS 148, Class 1A
- Federal VV-I-530A, Class II Specification
- GE A13A3A2 (10CA)
- IEEE
- International Standard IEC 60296
- NEMA Type II (obsolete)
- Westinghouse Specification PDS 55822AG

### **Features/Benefits**

- Excellent insulating properties
- High dielectric strength<sup>(1)</sup>
- Low power factor
- Resists oxidation and deposit formation
- Excellent low-temperature properties

## Inhibited Electrical Insulating Oil

**U.S. Technical Services Hot Line:**  
**1-800-255-9556**

**U.S. Customer Service:**  
**1-800-640-1956**

**International:**  
**+1-832-486-3363**

**E-mail address:**  
*conocolubricants@conocophillips.com*

[www.lubes.conoco.com](http://www.lubes.conoco.com)

600 N. Dairy Ashford • 2W9000 • Houston, TX 77079



- Compatible with materials used in transformers
- Does not contain any PCBs

<sup>(1)</sup> **Note:** In order to maintain its high dielectric strength for use as an insulating oil, the oil must be kept clean and dry. Contamination with even a small amount of water will significantly decrease the dielectric strength. The drums are sealed at the terminal with a blanket of dry air to keep moisture out. The drums should be stored indoors and covered to protect them from dust and debris. If stored outdoors, they should be positioned on their sides or upside down and covered to protect them from exposure to the elements. Every effort should be made to use the entire drum once the seal is broken to help prevent contamination. If contamination is suspected, always inspect the drum and test the oil for dielectric strength before use.

---

Due to continual product research and development, the information contained herein is subject to change without notification.

---

Copyright © 2007 ConocoPhillips Company. The ConocoPhillips logo, Conoco, and the Conoco logo are trademarks of ConocoPhillips Company in the U.S.A. and other countries.



**Transformer Oil**  
**Typical Properties**

| <b>ISO Grade</b>                                       | <b>10</b> |
|--|-----------|
| Density, g/cm <sup>3</sup> @ 15.6°C (60°F)             | 0.888     |
| Density, lbs/gal @ 15.6°C (60°F)                       | 7.39      |
| Color, ASTM D1500                                      | L 0.5     |
| Flash Point (COC), °C (°F)                             | 149 (300) |
| Autoignition Temperature, ASTM E659, °C (°F)           | 250 (482) |
| Pour Point, °C (°F)                                    | -50 (-58) |
| Viscosity,   |           |
| cSt @ 40°C   | 9.6       |
| cSt @ 100°C  | 2.3       |
| SUS @ 100°F  | 60        |
| SUS @ 210°F  | 34        |
| Viscosity Index  | 43        |
| Acid Number, ASTM D974, mg KOH/g                       | <0.01     |
| Aniline Point, ASTM D611, °C (°F)                      | 70 (158)  |
| Corrosive Sulfur, ASTM D1275, wt %                     | None      |
| Dielectric Strength, ASTM D877, kv <sup>(2)</sup>      | 39        |
| Interfacial Tension @ 25°C (77°F), ASTM D971, dynes/cm | 49        |
| Oxidation Stability, RPVOT, ASTM D2272, minutes        | 280       |
| PCB Content, ASTM D4059, wt %                          | None      |
| Power Factor @ 60 Hertz, ASTM D924,                    |           |
| @ 25°C (77°F)  | 0.003     |
| @ 100°C (212°F)  | 0.074     |
| Rust Test, ASTM D665 A&B                               | Pass      |
| Water, ASTM D6304, wt %                                | <0.003    |

<sup>(2)</sup> At the point of manufacture

### Health and Safety Information

For recommendations on safe handling and use of this product, please refer to the Material Safety Data Sheet via <http://w3.conocophillips.com/NetMSDS>.

Due to continual product research and development, the information contained herein is subject to change without notification.

Copyright © 2007 ConocoPhillips Company. The ConocoPhillips logo, Conoco, and the Conoco logo are trademarks of ConocoPhillips Company in the U.S.A. and other countries.