

August 19, 2008

P.O. Box 131359 • Tyler, Texas 75713, Phone 903.534.8021 • Fax 903.581.4376

Product Data Sheet



NOTE: The information in this publication is the result of careful testing in our laboratories, complemented by selected literature. It does not in any way constitute a guarantee, nor does it serve as a license to operate any patent. Due to widely varying conditions of product use, which are beyond our control, it is strongly recommended that the product be tested for suitability. Product typical properties in this publication are current as of August 19, 2008.

BIOBASED HIGH TEMP CHAIN LUBRICANT

ENVIROTECH CO-150 FG

*EnviroTech CO-150 FG is a specially developed, food grade chain lubricant blended from biobased oils and fortified with synthetic food grade white graphite. This unique high temperature formula lubricates at operating temperatures exceeding 1000°C and meets U.S.D.A. 1998 (H1) guidelines for applications where incidental food contact is possible. It does not contain VOCs and will out-perform other lubricants containing molybdenum disulfide, black graphite, or Teflon®. In addition, **EnviroTech CO-150 FG** contains a natural self-cleaning property which cleans the buildup on chains attributable to the use of inferior chain lubricants. This superior chain lubricant provides excellent protection against wear, rust, oxidation, and corrosion.*

APPLICATIONS: Use EnviroTech CO-150 FG for chains exposed to high service temperatures which exceed those recommended for conventional lubricants. This product is ideal for oven chains used in plants which produce bread, cookies, cakes and other baked food products. It is also suitable for can making where decorative coatings are being cured or applied. EnviroTech CO-150 FG can also be used in non-food grade high temperature applications.

Physical Properties

PRODUCT	CO-150 FG
ISO Viscosity Grade	150
Viscosity (ASTM D-445)	
@40°C	147.1 cSt
@100°C	24.9 cSt
Viscosity Index (ASTM D-2270)	203
Flash Point (ASTM D-92)	595°F/309°C
Fire Point (ASTM D-92)	640°F/335°C
Pour Point (ASTM D-97)	-25
Rust Prevention (ASTM D-665)	Pass
4 Ball Wear (ASTM D-2266)	0.40
4 Ball Weld (ASTM D-2783)	160 kg
NSF Registered	H1
ISO 21469	Pending
Kosher	Pending
Halal	Pending
CFIA	Pending

SPECIAL INSTRUCTIONS:

Because of the high concentration of white graphite in this chain oil, it needs agitation before use to insure even distribution of the solid lubricant. The white graphite has proven to stay in suspension for up to two weeks after being introduced into a capillary tube supplying lubricant to an applicator.