

November 20, 2006

P.O. Box 131359 • Tyler, CR 2120, Texas 75713, Phone 903.534.8021 • Fax 903.581.4376

# Product Data Sheet



NOTE: The information in this publication is the result of careful testing in our laboratories, complemented by selected literature. It does not in any way constitute a guarantee, nor does it serve as a license to operate any patent. Due to widely varying conditions of product use, which are beyond our control, it is strongly recommended that the product be tested for suitability. Product typical properties in this publication are current as of November 20, 006.

## SYNTHETIC BLEND

# NGP-CA SERIES

## Natural Gas Compressor

*Summit NGP-CA Series lubricants are synthetic blends formulated from highly refined hydrogenated paraffinic petroleum and high temperature synthetic base stocks. The addition of **SYNTHOLATE** inhibits the formation of varnish and carbon and provides superior thermal and oxidative stability. Utilizing the superior base stocks fortified with **SYNTHOLATE** extends the life of **Summit NGP-CA Series** lubricants compared to that of conventional mineral oils and provides the following money saving benefits:*

- *Reduces lubricant consumption - Extended drain intervals and lower vapor pressures reduce lubricant consumption.*
- *Reduces maintenance - **SYNTHOLATE** reduces carbon and varnish formation thus extending the time interval between overhauls.*
- *Excellent lubricity - Provides improved wear protection for bearings and other moving parts.*
- *Good compatibility - The base stocks and special additive package provide excellent compatibility with system components and inhibit against hydrogen sulfide corrosion.*
- *Improves safety - Higher flash points provide a greater margin of safety inspection results.*

## Physical Properties

PRODUCTS	100CA	150CA
ISO Viscosity Grade	100	150
Viscosity:		
@ 40°C, cSt	99.2	151.90
@ 100°C, cSt	11.38	14.92
Viscosity Index	101	98
Specific Gravity	0.876	0.879
Density		
@ 60°F, g/mL	0.871	0.875
@ 185°F, g/mL	0.827	0.831
Pour Point, °F (°C)	-25 (-32)	-22 (-30)
Flash Point, °F (°C)	495 (257)	495 (257)
Four Ball Wear Test, mm	0.6	0.6

### Thermal Characteristics:

#### Specific Heat

BTU/lbm - °F  
140°F = 0.476  
160°F = 0.485  
180°F = 0.494

#### Thermal Conductivity

BTU/hr - ft<sup>2</sup> and °F/inch  
0°F = 0.94  
200°F = 0.88  
400°F = 0.83